

PSV-22

Vacuum pump oil



Your benefits at a glance

- Excellent water separation
- Protection against wear, rust and corrosion

Your requirements - our solution

Summit PSV-22 is formulated from a vacuum distilled ultrapure paraffinic hydrocarbon base stock to provide an extremely low vapor pressure vacuum pump lubricant. This non-foaming fluid has excellent water separation and provides protection against wear, rust and corrosion.

PSV-22 is an extended life lubricant designed to function in recirculating systems such as liquid ring vacuum pumps which are subject to severe temperature and environmental conditions.

Material safety data sheets

Material safety data sheets can be requested via our website <https://www.klsummit.com>. You may also obtain them through your contact person at Summit Lubrication.

Characteristics	PSV-22
Article number	340112
Demulsifying capacity	40/38/2 (10) (min)
Density	0.86 g/cm ³
Flash point	193 °C
Kinematic viscosity, 100°C	4.2 mm ² /s
Kinematic viscosity, 40°C	21.9 mm ² /s
Viscosity index	103
Copper corrosion	1 - - corrosion degree
Pour point, DIN ISO 3016, ASTM D97, ASTM D5950, ASTM D7346, based on standard	-33 °C
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months

PSV-22

Vacuum pump oil



Summit Lubrication

Your expert in specialty lubricants. Since 1982, we have partnered with you to bring you the right solution and advanced lubrication technologies. With over 500 products, from air and gas compressor oils to refrigeration oils, we develop top-of-the-line products tailored to your specific needs. Your success is our success.

Summit Lubrication a brand of Klüber Lubrication NA LP /
9010 County Road 2120, Tyler, TX 75707 /
Phone: +1 800 749 5823 / www.klsupport.com

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication NA LP. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication NA LP and if source is indicated and voucher copy is forwarded.